

ERADUR[®] WB

Product type:	Two-component, water-dilutable, solvent-free epoxy coating.	
Application areas:	Topcoat. Adhesion primer for concrete surfaces before painting, coating etc	
Properties:	Abrasion-resistant and diffusion-open epoxy paint. Very good adhesion to most substrates, even cured epoxy. Short drying and curing time. Cures at 10 ° C. Withstands early water load. Great for dust binding. The colors have very good covering ability. The product does not emit odors or flavors, and is not flammable.	
Application temperature:	Application temp (floor temp): 10-35 °C. Make sure the ventilation is good.	
Pot life:	Pot life after mixing is approximately 60 min.	
Curing time:	1-4 hours before the application of coating or painting. 6-12 hours for pedestrians and lower loading (depending on temperature). 2-4 days for complete curing and resistance.	
Mixing ratios:	1 part by weight of ERADUR WB, Comp A (2,3 kg) 3 parts by weight of ERADUR WB, Comp B (7,7 kg) Base and hardener must be mixed very well before dilution with water can be done. Dilute with water while stirring. Depending on the working method, the room temperature and type of surface (floor, ceiling, wall) dilution with approx 10% in 1st stroke and 5% in the finishing stroke. <i>ERADUR is a two-component product, and an insufficient mixing will result in partially incomplete curing. Mix for several minutes with a machine just before the application, make sure that all material in the bottom and rim of the container is properly mixed.</i> <i>Keep the exact mixing ratio between component A and B. All materials should preferably have ambient temperature before use.</i>	
Safety:	Wear safety goggles and protective clothing during mixing and application. Read the label and safety data sheet before using the product.	
Technical specification:	Density	base: 1,15 gr/cm ³ hardener: 1,28 gr/cm ³ mixture: 1,25 gr/cm ³
	Viscosity	about 0,4 Pa s (after dilution with water)
	Solid content	50%
	Gloss	blank
	Shelf life	6 months in an unbroken container (15 °C).