

ERADUR[®] SPACKEL T

Product type:	Two-component, solvent-free, epoxy-plaster. Dry content 100%,	
Application areas:	Repair of damage in concrete. Leveling and plastering of floor and wall. It can also be used for bonding and covered skirting.	
Properties:	<ul style="list-style-type: none">• Thixotropic plaster that can be applied in thick layers without shrinking or "sacking".• The product is low in weight and can be ground.• Good adhesion to most mineral substrates.	
Application temperature:	Application temp (floor temp): 8-30 °C. Can be adapted to lower / higher application temperature.	
Pot life:	Pot life after mixing is approximately 30 min.	
Curing time:	1 day for loading. 5-10 days for complete curing and resistance.	
Mixing ratios:	4 parts by weight of ERADUR SPACKEL T, Comp A (2 kg) 1 part by weight of ERADUR SPACKEL T, Comp B (0,5 kg) <i>ERADUR is a two-component product, and an insufficient mixing will result in partially incomplete curing. Mix for several minutes with a machine just before the application, make sure that all material in the bottom and rim of the container is properly mixed.</i> <i>Keep the exact mixing ratio between component A and B.</i> <i>All materials should preferably have ambient temperature before use.</i>	
Safety:	Wear safety goggles and protective clothing during mixing and application. Read the label and safety data sheet before using the product.	
Technical specification:	Tensile strength	ca 10 N/mm ² i.e. fracture in concrete
	Compressive strength	ca 30 N/mm ²
	Density	mixture: 1,5 gr/cm ³
	Viscosity	about 0,4 Pa s
	Solid content	100%
	Shelf life	6 months in an unbroken container (> 15 °C).