

# ERADUR<sup>®</sup> FLEXIBEL PRIMER

<b>Product type:</b>	Two-component, solvent-free, flexible unpigmented epoxy coating.	
<b>Application areas:</b>	Adhesives for seamless floorings with color quartz sand. Adhesives for epoxy use. Dust binding etc.	
<b>Properties:</b>	<ul style="list-style-type: none"><li>• Primer for coatings on failing surfaces, particle board etc.</li><li>• Sound / vibration damping on floorboard etc.</li><li>• Also suitable as a primer on asphalt and bitumen substrates.</li></ul>	
<b>Application temperature:</b>	Application temp (floor temp): 15-25 °C. (RF < 80%)	
<b>Pot life:</b>	Pot life after mixing is approximately 40-60 min, depending on the temperature.	
<b>Curing time:</b>	8-16 hours before the application of coating or painting. 24 hours for pedestrians and lower loading (depending on temperature). 5-7 days for complete curing and resistance.	
<b>Mixing ratios:</b>	2 parts by weight of ERADUR FLEXIBEL PRIMER, Comp A (10 kg) 1 part by weight of ERADUR FLEXIBEL PRIMER, Comp B (5 kg)  <i>ERADUR is a two-component product, and an insufficient mixing will result in partially incomplete curing. Mix for several minutes with a machine just before the application, make sure that all material in the bottom and rim of the container is properly mixed.</i>  <i>Keep the exact mixing ratio between component A and B. All materials should preferably have ambient temperature before use.</i>	
<b>Safety:</b>	Wear safety goggles and protective clothing during mixing and application. Read the label and safety data sheet before using the product.	
<b>Technical specification:</b>	Shore D	ca 45
	Density	mixture: 1,07-1,18 gr/cm <sup>3</sup> (klar pigm.)
	Viscosity	about 1,0 Pa s
	Solid content	100%
	Gloss	Blank
	Shelf life	6 months in an unbroken container (> 15 °C).