

ERADUR[®] BINDER TIX

Product type: Two-component, thixotropic, solvent-free epoxy coating.

Application areas: Tixotrop, topcoat, intended for application to walls, plinths, etc.

Properties:

- Good mechanical properties.
- Low yellowing and good lightfastness.
- Very good resistance to inorganic acids, alkali, gasoline, oils.

A clear lacquer formulated for use as a topcoat on plinths, bases, and walls where high demands exist on low yellowing, high light fastness in combination with abrasion resistance and wear resistance. The product does not emit odors or flavors and is not flammable. Otherwise, the product has the same properties as Eradur Topplack.

Application temperature: Application temp (floor temp): 15-30 °C.

Pot life: Pot life after mixing is approximately 30 min.

Curing time: 8-16 hours before the application of coating or painting.
24-48 hours for pedestrians and lower loading (depending on temperature).
5-7 days for complete curing and resistance.

Mixing ratios: 2,24 parts by weight of ERADUR BINDER TIX, Comp A (11,2 kg)
1 part by weight of ERADUR BINDER TIX, Comp B (5 kg)

ERADUR is a two-component product, and an insufficient mixing will result in a partially incomplete curing. Mix for several minutes with a machine just before the application, make sure that all material in the bottom and rim of the container is properly mixed.

*Keep the exact mixing ratio between component A and B.
All materials should preferably have ambient temperature before use.*

Safety: Wear safety goggles and protective clothing during mixing and application. Read the label and safety data sheet before using the product.

Technical specification:	Density	base: 1,11 gr/cm ³ Harder: 1,01 gr/cm ³
	Viscosity	Tixotrop
	Solid content	100%
	Gloss	Blank
	Shelf life	6 months in an unbroken container (> 15 °C).