

ERADUR[®] BINDER

Product type:	Two-component, solvent-free, semi-elastic pigmented epoxy coating. Dry content 100%, gives a colorless, glossy and dense surface.	
Application areas:	Adhesives for seamless floorings with color quartz sand. Adhesives for epoxy use. Dust binding etc.	
Properties:	<ul style="list-style-type: none">• Low viscous formulation specially adapted for color sand floors.• Adhesives for sand in epoxy use and screeds.• Primer for concrete surfaces before painting, coating, and carpet. <p>Very good penetration and adhesion to concrete and other mineral substrates. Reinforces the concrete surface. Excellent for dust binding gives the concrete a dense, durable, chemical resistant surface.</p>	
Application temperature:	Application temp (floor temp): 15-30 °C.	
Pot life:	Pot life after mixing is approximately 40-60 min, depending on the temperature.	
Curing time:	8-16 hours before the application of coating or painting. 24-48 hours for pedestrians and lower loading (depending on temperature). 5-7 days for complete curing and resistance.	
Mixing ratios:	2 parts by weight of ERADUR BINDER, Comp A (10 kg) 1 part by weight of ERADUR BINDER, Comp B (5 kg)	
	<i>ERADUR is a two-component product, and an insufficient mixing will result in partially incomplete curing. Mix for several minutes with a machine just before the application, make sure that all material in the bottom and rim of the container is properly mixed.</i>	
	<i>Keep the exact mixing ratio between component A and B. All materials should preferably have ambient temperature before use.</i>	
Safety:	Wear safety goggles and protective clothing during mixing and application. Read the label and safety data sheet before using the product.	
Technical specification:	Tensile strength	ca 35 N/mm ² i.e. fracture in concrete
	Compressive strength	ca 50 N/mm ²
	Density	base: 1,12 gr/cm ³ Harder: 1,01 gr/cm ³ mixture: 1,08 gr/cm ³
	Viscosity	about 0,4 Pa s
	Solid content	100%
	Gloss	High gloss
	Shelf life	6 months in an unbroken container (> 15 °C).