

# DEGADUR® HÄRDARPULVER

Hardener Amount in weight percent:

Product	1 °C	5 °C	10 °C	15 °C	20 °C	25 °C	30 °C	35 °C
Ecryl Flex		5,0	4,0		2,0		1,0	
Ecryl FlexTop			2,5		1,5			1,0
Ecryl HardTop		1,8	1,5	1,0	0,8			
Ecryl Hålkälspasta	5,0		4,0		2,5	2,0	1,5	
Ecryl L2Top			1,5		1,5	1,0	1,0	
Ecryl LP		4,5	3,0	2,5	2,0		1,0	
Ecryl LPI 51		4,0	3,0		2,0		1,5	
Ecryl LPWW		4,5	3,0		2,0		1,0	
Ecryl Membran		5,0	4,0		2,0		1,0	
Ecryl Primer W	3,3	2,0	1,5	1,2	1,0	0,7		
Ecryl Primer		6,0	5,0		3,0		2,0	
Ecryl WWTop		1,5	1,5		1,0	1,0		

The hardener amount is calculated on the binder used.

Temperature is attributed to binder, floor and air temperature.

The hardener amount for Degadur® III is calculated according to binder + filler.

Degadur® 529 can be used at 0 °C using 0.5% Degadur® Accelerator 101 and 4.5% Degadur® Hardener Powder.