

# ERADUR<sup>®</sup> MASSIV SL

<b>Product type:</b>	Two-component, solvent-free, pigmented epoxy coating. Adhesive Component in Eradur Massiv SL and Eradur Struktur when performed as monochrome.																
<b>Application areas:</b>	<ul style="list-style-type: none"><li>- Thick film painting: 0.5 - 1 mm</li><li>- Self-leveling coatings: 2 - 5 mm.</li><li>- Pigmented sand coatings: 3 - 15 mm.</li></ul>																
<b>Properties:</b>	<p>It provides a hard, durable and non-porous surface that can be adapted to the requirements of slip-resistance. The adhesion to concrete and other mineral substrates is good. The coating provides a distribution of point loads at thicknesses above 4 mm.</p> <p>Good chemical-resistance. Withstands gasoline, oils grease, salts, water, etc. Limited resistance to strong acids and strong solvents. The resistance to alkali and lye is good. Eradur Massiv SL is odorless and not flammable.</p>																
<b>Application temperature:</b>	Application temp (floor temp): 12-25 °C. (RF < 80% Air, RF < 93% Concrete). Can also be applied at other temperatures, but requires a special hardener.																
<b>Pot life:</b>	Pot life after mixing is approximately 40 min.																
<b>Curing time:</b>	<p>12-16 hours for pedestrians and lower loading. 5-7 days for complete curing and resistance.</p> <p>Several curing agents with different curing properties are available, e.g.</p> <ul style="list-style-type: none"><li>- Massiv SL, B provides the best possible flow properties with slow curing.</li><li>- Massiv SL LE, B provides a low emission coating.</li><li>- Massiv SL U, B provides a curing time of about 4-6 hours</li></ul>																
<b>Mixing ratios:</b>	<p>Base: 3,41 parts by weight of ERADUR Massiv SL, Comp A (11,6 kg) Hardener: 1 part by weight of ERADUR Massiv SL, Comp B (3,4 kg) Filler: 4,41 parts by weight of ERADUR Massiv SL, Comp C (15 kg) (Comp C only used for self-leveling coatings).</p> <p><i>ERADUR is a two-component product, and an insufficient mixing will result in partially incomplete curing. Mix for several minutes with a machine just before the application, make sure that all material in the bottom and rim of the container is properly mixed.</i></p> <p><i>Keep the exact mixing ratio between component A and B.</i> <i>All materials should preferably have ambient temperature before use.</i></p>																
<b>Safety:</b>	Wear safety goggles and protective clothing during mixing and application. Read the label and safety data sheet before using the product.																
<b>Technical specification:</b>	<table><tr><td>Compressive strength</td><td>ca 87 MPa</td></tr><tr><td>Tensile strength</td><td>ca 41 MPa, i.e. fracture in concrete</td></tr><tr><td>Flexural strength</td><td>ca 27 MPa</td></tr><tr><td>Shore D</td><td>ca 82</td></tr><tr><td>Solid content</td><td>100%</td></tr><tr><td>Gloss</td><td>Blank</td></tr><tr><td>Consumption</td><td>ca 0,3 kg/m<sup>2</sup></td></tr><tr><td>Shelf life</td><td>6 months in an unbroken container (&gt; 15 °C).</td></tr></table>	Compressive strength	ca 87 MPa	Tensile strength	ca 41 MPa, i.e. fracture in concrete	Flexural strength	ca 27 MPa	Shore D	ca 82	Solid content	100%	Gloss	Blank	Consumption	ca 0,3 kg/m <sup>2</sup>	Shelf life	6 months in an unbroken container (> 15 °C).
Compressive strength	ca 87 MPa																
Tensile strength	ca 41 MPa, i.e. fracture in concrete																
Flexural strength	ca 27 MPa																
Shore D	ca 82																
Solid content	100%																
Gloss	Blank																
Consumption	ca 0,3 kg/m <sup>2</sup>																
Shelf life	6 months in an unbroken container (> 15 °C).																