## ERADUR<sup>®</sup> PU PARKING TOP

Product type <i>:</i>	Two-component, solvent-free, pigmented polyurethane pulp.	
Application areas: Properties:	<ul> <li>self-leveling solid (seamless) coatings of 2-6 mm.</li> <li>Pigmented sand coatings of 3-12 mm.</li> <li>Thick film painting of 0.3-1 mm on concrete substrate</li> <li>Good mechanical properties.</li> </ul>	
	<ul> <li>Good resistance to ind</li> <li>Good resistance to stro</li> <li>Heat resistant, TG&gt; I Darkens and yellows in</li> </ul>	ustrial chemicals. ong inorganic and organic acids. 10°C, withstands hot water and steam cleaning. n UV light.
Application temperature:	<ul> <li>Does not emit odors or flavors, is not flammable.</li> <li>Provides a safe and trouble-free curing between 15-30°C.</li> <li>Is sensitive to high humidity during application and curing.</li> <li>RF &lt;85% (20°C).</li> </ul>	
Pot life:	Pot life after mixing is approximately 30 min.	
Curing time:	<ul><li>16 hours for foot traffic</li><li>2–3 days for light loads.</li><li>3 days for full curing and chemical resistance.</li></ul>	
Mixing ratios:	ERADUR PU PARKING TOP comp A (15 kg) ERADUR PU PARKING TOP comp B (4,5 kg)	
	ERADUR is a two-component product, and an insufficient mixing will result in partially incomplete curing. Mix for several minutes with a machine just before the application, make sure that all material in the bottom and rim of the container is properly mixed.	
	Keep the exact mixing ratio between component A and B. All materials should preferably have ambient temperature before use.	
Safety:	Wear safety goggles and protective clothing during mixing and application. Read the label and safety data sheet before using the product.	
Technical specification:	Tensile strength Bending strength Compressive strength Density Viscosity Solid content Gloss Shelf life	ca 20 MPa ca 30 MPa ca 54 MPa base: 1,4 gr/cm <sup>3</sup> about 1,2 Pa s 100% Blank 6 months in an unbroken container (>15°C).

SEAMLESS FLOORING

Tel 042-29 22 50 www.eradur.com info@eradur.com