

# ERADUR® WB

<b>Product type:</b>	Two-component, water-dilutable, solvent-free epoxy coating.		
<b>Application areas:</b>	Topcoat. Adhesion primer for concrete surfaces before painting, coating etc.		
<b>Properties:</b>	Abrasion-resistant and diffusion-open epoxy paint. Very good adhesion to most substrates, even cured epoxy. Short drying and curing time. Cures at 10°C. Withstands early water load. Great for dust binding. The colors have very good covering ability. The product does not emit odors, and is not flammable.		
<b>Application temperature:</b>	Application temp (floor temp): 15-35°C. Make sure the ventilation is good.		
<b>Pot life:</b>	Pot life after mixing is approximately 60 min.		
<b>Curing time:</b>	1-4 hours before the application of coating or painting. 6-12 hours for pedestrians and lower loading (depending on temperature). 2-4 days for complete curing and resistance.		
<b>Mixing ratios:</b>	1 part by weight of ERADUR WB    comp A (2,3 kg) 3 parts by weight of ERADUR WB    comp B (7,7 kg)  Base and hardener must be mixed very well before dilution with water can be done. Dilute with water while stirring. Depending on the working method, the temperature of the room and the type of surface (floor, ceiling, wall), dilution with approximately 10% in the Base Layer and 5% in the Top Layer is recommended. If a lower form of diffusion-open surface is desired, apply a layer of undiluted WB as a top.  Eratur WB is a two-component product, which means that a poor mixture will result in a partially uncured coating. Therefore, mix thoroughly for several minutes against the bottom and edges of the container with a machine just before application.  It is important that the mixing ratio between base and hardener is exact.  Base, hardener and filler material should be at room temperature when used. Wear safety goggles and protective clothing during mixing and application. Read the label and safety data sheet before using the product.		
<b>Safety:</b>			
<b>Technical specification:</b>	Density	base: 1,15 gr/cm <sup>3</sup> hardener: 1,28 gr/cm <sup>3</sup> mixture: 1,25 gr/cm <sup>3</sup>	UK-13.06.2025
	Viscosity	about 0,4 Pa s (after dilution with water)	
	Solid content	50%	
	Gloss	blank	
	Consumption	2 x 0.15 l/m <sup>2</sup> (i.e. 2 layers)	
	Shelf life	6 months in an unbroken container (15°C).	

*Dessa anvisningar och råd är givna utifrån våra egna erfarenheter av produkterna. Då arbetsutförandet ligger utanför vår kontroll begränsas vårt ansvar till materialets kvalitet. Vår erfarenhet och kunskap om produkterna är naturligtvis bredare än vad som här låter sig beskrivas. Kontakta oss gärna för mer information eller gå in på vår hemsida.*